


Vulmproepox TC



Anti-corrosion top coat

Product description:

Vulmproepox TC is a two-component coating material based on water. It can be used as a topcoat for steel. It consists of component A (aqueous dispersion, epoxy resin containing additives, pigments and fillers) and component B (polyamide hardener).

Use:

It is used as coating for metal structures (also from light metals and alloys) as an anti-corrosion protection with a high degree of corrosion inhibition and as a protection against chemical and mechanical effects. **Vulmproepox TC** is recommended for surfaces in marine environments (salinity, category C-4), such as the interior of ships, steel structures, bridges, indoor walls and warehouse and factory premises, steel doors, chemical plants, swimming pools, shipyards and docks on the seashore.

Benefits:

- resilient and hard surface
- high mechanical resistance
- extreme resistance to impacts and shocks
- good chemical and mechanical resistance
- resists penetration of liquids
- adhesive even to a slightly greasy surface
- possibility to achieve a greater thickness in one coating

Test data:

- | | |
|---------------|-----------------------------|
| TSÚS 353/2005 | STN EN ISO 6270-1 (67 2012) |
| | STN EN ISO 2808 (67 3061) |
| | STN EN 2409 (67 3085) |
| | STN EN ISO 7253 (67 3092) |
- corrosion in the cross-section by a method according to Annex A, STN EN ISO 12944-6
 - Test report no. 90-08-0247

Product data:

- | | |
|-------------|---|
| colour: | RAL according to customer's choice |
| appearance: | matte, semi-gloss |
| shelf life: | 12 months in original packaging in dry conditions
at the temperature 10 – 35 °C |
| limit VOC: | according to Ministry of Environment Decree no. 127/2011 Coll.: 200 g/l
measured value: 12,4 g/l |

Physical data:

- | | |
|-----------------|---------|
| binder content: | 20 % |
| solids content: | 65 % |
| water content: | 15 % |
| flow: | 15,9 cm |

hardness:	after 24 hours	60 Shore D
	3 days	70 Shore D
	7 days	78 Shore D
	28 days	82 Shore D
	at a relative air humidity of 65 % and temperature of 20 °C	
abrasion resistance:	156 md/1000 cycles	
handling time:	45 minutes	
density:		
component A:	2,37 g/ml	
component B:	1,08 g/ml	
component A + B:	2,07 g/ml	

Processing temperature:

minimum temperature of the substrate:	5 °C
maximum temperature of the substrate:	30 °C
ideal temperature for processing:	20 °C
maximum relative air humidity:	85 %

Theoretical capacity:

6,7 – 10 m ² /kg	1x coating thickness 80 µm
2,2 – 3,3 m ² /kg	2 – 3x coating thickness 250 µm

Application methods:

roller, brush, spray

Instructions for use:

The mixture of components A and B is in a ratio of 10 : 2 (by weight – 1 kg of component A and 0.2 kg of component B). Mixing of the reactive components takes 2 – 3 minutes, but ends after achieving a homogeneous mixture. Viscosity is adjusted by the addition of water (max. 10 – 15 %). The prepared material is applied by brush, roller or spray, independently of the thickness of layer. The material should be applied within 45 minutes after mixing, since afterwards it begins to solidify.

The coating is applied in a single layer.

Substrate:

The substrate must be sufficiently coherent and supporting. Surface must be flat, solid, free of dirt and loose particles. The coating can be applied on slightly oily surfaces. Surface must be dusted and without rough particles, preferably cleaned by pressurized water. Degreasing is not necessary.

Time data for application:

processability of the mixed material:	approx. 45 minutes
dry to touch and re-coating interval:	approx. 2 hours
walkable:	24 hours
fully loadable:	65 hours
at a relative air humidity of 65 % and temperature of 20 °C	


Cleaning of tools:

Immediately after use, with water.

Resistance:

- withstands high mechanical loads
- resistant to chemicals, solvents, detergents and cleaners
- resistant to heat of up to 140 °C (short-term), does not change characteristics at 100 °C
- corrosion resistant (category C3 (long durability) and C4 (medium durability))

Chemical resistance:



Safety:

Vulmproepox TC – when handling, proceed in accordance with the general safety measures, follow the safety instructions on the packaging labels and on safety data sheets. Data, specifications, directions and recommendations given in this technical data sheet are based on experience gained in modeling of supposed ways of applications, or under specially defined conditions. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by the user. The manufacturer and distributor are not responsible for the results achieved, loss, direct or consequential damages arising from failure to comply with the recommended use of the product, which go beyond the conditions herein.

Tests:

Property	Rule for determining compliance	Determined comparative value	Test report identification
Release of pollutants into the environment (V)	Ministry of Environment Decree no. 515/2001 Coll.	Safety Data Sheet	Safety Data Sheet
Corrosion resistance	STN EN ISO 12944 – 6	C4 – high durability	Test Report no. 90-08-0247, TSÚS, branch Tatranská Štrba, 24.10.2008
Cross-cut adhesion	STN EN ISO 12944 – 6	Degree 0-1	Test Report no. 90-08-0247, TSÚS, branch Tatranská Štrba, 24.10.2008

Note: Properties, which – in accordance with the technical specifications – may be tested only by a competent authorized person, are indicated by the symbol (AO).

More details are given in the test report no. 90-08-0247, tests: corrosion resistance, cross-cut adhesion, TSÚS n.o., branch Tatranská Štrba, 24.10.2008